



KUREZ DR-100

LOW VOC, DISSIPATING CURING COMPOUND

PACKAGING

55 gal (208 L) drums (MTO)
Code: 156D 55

5 gal (18.9 L) pails (MTO)
Code: 156D 05

CLEAN UP

Warm, soapy water
(see "Clean-Up and Removal")

SHELF LIFE

2 years when stored properly

SPECIFICATIONS AND COMPLIANCES

- VOC Content: 98 g/L
- ASTM C309, Types 1 and 1-D, Classes A & B
- AASHTO M 148, Types 1 and 1-D, Classes A & B

DESCRIPTION

KUREZ DR-100 is a water-based resin, liquid membrane-forming curing compound that provides an excellent initial cure for concrete, then begins to break down and deteriorate upon exposure to traffic and UV light. After simple cleaning to completely remove the KUREZ DR-100, the concrete is ready to receive application of coverings, coatings, or sealers. With a VOC content of less than 100 g/L, KUREZ DR-100 is fully VOC-compliant in the U.S. and Canada, even in the highly regulated air quality districts of California.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Use of this product ensures proper curing resulting in stronger, more wear-resistant concrete
- Helps to minimize dusting
- Available in a fugitive dye formulation
- Film breaks down when exposed to UV & traffic
- IMPROVED FORMULA
- Dries leaving a clearer film
- Easier to remove
- Lower odor
- Lower viscosity - easier to spray

COMMON METHODS

- Industrial pump-up sprayer or an airless industrial sprayer
- Short-nap roller

PRIMARY APPLICATIONS

- Interior or exterior concrete
- Concrete that will later receive a covering or coating
- Where a long term membrane film is not desired on the concrete surface

APPEARANCE

The color of KUREZ DR-100 may vary from white to off white. Color variation does not affect product performance. KUREZ DR-100 will turn a deeper amber color upon exposure to UV light.

APPLICATION PROPERTIES

These properties are based on laboratory conditions at at 73°F, 50% RH. Expect variation based on jobsite conditions.

Drying time:	1 hour
Foot Traffic:	2 to 4 hours
Wheel Traffic:	6 to 10 hours
Moisture Loss (ASTM C156):	< 0.55 kg/m ²

COVERAGE

For good dissipation and easy removal, do not apply at a thicker film than indicated.

Textured Concrete:	300 ft ² /gal (7.4 m ² /L)
Smooth Concrete:	400 ft ² /gal (9.8 m ² /L)

DIRECTIONS FOR USE

Surface Preparation: As soon as possible after final troweling (or stripping of forms in vertical applications), apply KUREZ DR-100 at the recommended coverage rate.

Mixing: Material may separate during long term storage. Mild agitation or mixing is required before use.

Application: Apply at a uniform coverage by spray or roller application. Product may be sprayed with a hand held "pump-up" sprayer or an airless industrial sprayer. On vertical surfaces such as walls and columns, KUREZ DR-100 should be applied immediately after forms are stripped. Do not apply at a thicker film than the suggested coverage rates allow. Heavy or uneven application can result in slow dissipation and difficult removal of the KUREZ DR-100, and may discolor the concrete surface. On interior hard troweled floors where a liquid densifier will be applied (and with approval from the project engineer), the coverage rate of KUREZ DR-100 may be increased to 400 ft²/gal (9.8 m²/L) in order to facilitate easier removal.

Dissipation: The exact time for dissipation/break down of KUREZ DR-100 will vary depending on application rate, moisture level in the concrete, and the amount of exposure to UV light and construction traffic. KUREZ DR-100 will continue to dissipate and become increasingly easier to remove as time passes. **Floors to receive coatings, sealers and coverings must be cleaned thoroughly to ensure complete removal of KUREZ DR-100.**

CLEAN-UP AND REMOVAL

Clean tools and equipment with warm, soapy water before KUREZ DR-100 dries.

The use of a heavy-duty floor cleaner such as EUCO CLEAN & STRIP is recommended to aid cleaning and removal. Scrub the floor with the cleaner and stiff bristle mechanical equipment, then rinse well with clean water. Heavy-duty mechanical means may also be used for removal, such as heavy-duty water blasting or abrasive methods like sanding or grinding. After proper clean-up, follow the instructions of the sealer, coating or covering manufacturer for the recommended surface preparation for the particular product to be applied. The use of KUREZ DR-100 does not eliminate the need to adequately clean and prepare the surface to assure good adhesion of the applied product, particularly when concrete or terrazzo toppings are to follow.

PRECAUTIONS/LIMITATIONS

- Do not allow containers of this product to freeze.
- Store between 50 °F to 100 °F (10 °C to 38 °C).
- For best application results, product temperature should be between 50 °F to 90 °F (10 °C to 32 °C) with ambient and surface temperatures between 45 °F to 100 °F (7 °C to 38 °C).
- After application, KUREZ DR-100 must remain uncovered and unprotected for proper dissipation.
- Do not apply at temperatures below 40 °F (4 °C).
- Do not use as bond breaker for tilt-up construction.
- Do not subject to rain or water for 12 hours after application.
- Not intended for use on architectural concrete panels unless complete removal is planned.
- Do not thin this product with water or other solvents.
- Longer dissipation times can be expected if the product is not exposed to traffic & sunlight or if the product is applied heavier than recommended.
- Film may slightly discolor when exposed to sunlight
- In all cases, consult the Safety Data Sheet before use.

Rev. 03.22

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.