

## PRODUCT DATA SHEET

# Sikagard®-200 HD WB

(formerly MKure HD 200WB)

HARDENING, SEALING AND DUSTPROOFING COMPOUND

#### PRODUCT DESCRIPTION

Sikagard®-200 HD WB is a water-soluble, inorganic, silicate-based curing, hardening, sealing and dustproofing compound. Use it for freshly placed and finished concrete and in the renovation of aged concrete.

#### **USES**

- Interior and exterior
- Above or below grade
- Concrete floors and pavements
- Curing of fresh concrete
- Renovation of aged concrete

## **CHARACTERISTICS / ADVANTAGES**

- Protects floors during construction
- Easy to apply and quick drying for quick turnaround
- Water-based; no VOCs and easy to clean up
- Aids curing of concrete; minimizes shrinkage cracking and improves strength development
- Hardens concrete to withstand moderately heavy-duty traffic
- Improved abrasion resistance to extend wearability

## **APPROVALS / STANDARDS**

USDA compliant for use in meat and poultry areas

#### PRODUCT INFORMATION

Chemical Base	Sikagard®-200 HD WB is an alkalisilicate hardener.	
Packaging	5-gallon (18.9 L) pails 55-gallon (208 L) drums	
Shelf Life	15 months when properly stored.	
Storage Conditions	Store in unopened containers in a cool, dry area between 35°F and 85°F (4°C and 29°C). Keep from freezing.	
Color	Clear	

Product Data Sheet
Sikagard®-200 HD WB
September 2024, Version 02.01
020815110010000059

## **TECHNICAL INFORMATION**

Abrasion Resistance	Untreated sample	8 g loss 1,000 g load, revolutions(100%)	1,000 (Taber Abraser CS-1 Whee	
	Sikagard®-200 HD WB	6 g loss 1,000 g load,	1,000	
	treated*	revolutions (78%)	· 	
	20% increase in abrasion resistance over untreated samples *Application to fresh mortar. Abrasion resistance measured at 7 days, 70° F (23° C) and 50% relative humidity.			
Water retention	Untreated sample	90 g loss	(ASTM C156	
	Sikagard®-200 HD WB treated*	63 g loss		
	30% improvement in moisture rete *Application to fresh mortar. Abra:		D° F (23° C) and 50% relative humidity.	
Chemical Resistance	Alkali-silicate hardeners can be used to increase resistance to chemicals including (but not limited to) the following:			
	Acetic acid, <10%	Cresol	Paraffin	
	Aluminum sulfate	Cumol	Peanut oil	
	Ammonium carbonate	Ethyl alcohol	Phenanthrene	
	Ammonium chloride	Ferric chloride	Phenol, 25%	
	Ammonium hydroxide	Ferric nitrate	Phosphoric acid, 80%	
	Ammonium nitrate	Ferric sulfate	Poppy seed oil	
	Ammonium sulfate	Fish oil	Potassium aluminum sulfate	
	Anthracene	Formaldehyde, 37%	Potassium carbonate	
	Arsenious acid	Formic acid, 90%	Potassium chloride	
	Barium hydroxide	Fruit juices	Potassium dichromate	
	Beef fat	Glucose	Potassium hydroxide, 15%	
	Benzene	Glycerine	Potassium nitrate	
	Borax	Honey	Potassium persulfate	
	Boric acid	Humic acid	Potassium sulfate	
	Buttermilk	Hydrochloric acid, 10%	Rapeseed oil	
	Calcium chloride	Hydrogen sulfide	Rosin	
	Calcium hydroxide	lodine	Sea water	
	Calcium nitrate	Lactic acid, 25%	Sodium bicarbonate	
	Calcium sulfate	Lead nitrate	Sodium bromide	
	Carbazole	Lead-refining solutions, 10%	Sodium carbonate	
	Carbonic acid	Lignite oils	Sodium chloride	
	Castor oil	Linseed oil	Sodium dichromate	
	China wood oil	Machine oil	Sodium hydroxide, 10%	
	Chromic acid, 10%	Magnesium chloride	Sodium nitrate	
	Chrysen	Magnesium nitrate	Sodium nitrite	
	Cider	Manure	Sodium sulfate	
	Coal	Methyl alcohol	Sodium sulfite	
	Coal-tar oils	Mine water, waste	Sodium thiosulfate	
	Cobalt sulfate	Mineral spirits	Soybean oil	
	Coconut oil	Molasses	Sugar	
	Copper chloride	Mustard oil	Sulfur dioxide	
	Copper sulfate	Nickel sulfate	Toluene	
	Corn syrup	Nitric acid, 40%	Zinc chloride	
	Cottonseed oil	Oleic acid, 100%	Zinc nitrate	
	Creosote	Olive oil	Zinc sulfate	

Product Data Sheet Sikagard®-200 HD WB September 2024, Version 02.01 020815110010000059



#### APPLICATION INFORMATION

Coverage	150–200 ft $^2$ /gal (3.68 – 4.9 m $^2$ /L) Coverage may vary with application method, surface conditions, and porosity
Drying Time	<ol> <li>Sikagard®-200 HD WB penetrates in approximately 30-60 minutes after application, depending on temperature, humidity, and job conditions. Each application must penetrate thoroughly before proceeding with the next.</li> <li>A floor treated with Sikagard®-200 HD WB must completely dry before accepting any traffic. Allow 24 hours before subjecting to heavy traffic.</li> </ol>

### **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## **ENVIRONMENTAL, HEALTH AND SAFETY**

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

#### **APPLICATION INSTRUCTIONS**

#### For Best Performance

- On exterior applications, rapid drying conditions may greatly reduce the effectiveness of Sikagard®-200 HD WB as a curing aid. It is the responsibility of the user to adjust the curing rate to properly regulate the hydration of the concrete.
- If Sikagard®-200 HD WB freezes, warm and restir to uniformity. If separation is persistent, discard product.
- Install joint sealants before application of Sikagard®-200 HD WB; if not possible, test first for adhesion.
- For subsequent coating applications, perform proper surface preparation and consult the coatings manufacturer for more instructions.
- Spray application will yield best results.
- Dry buffing 24 hours after application will improve sheen of finished floor.
- Application method and concrete porosity will affect final appearance of Sikagard®-200 HD WB. White residue signifies too strong a mix or the surface reaching maximum hardness. Applications should be stopped and the surface flushed with clean hot water, scrubbed with a stiff-bristled broom and allowed to dry. If any applications remain, dilution of the product may be required to prevent whitening.
- Applications to concrete containing pozzolanic additives will require additional Sikagard®-200 HD WB.
- Do not allow Sikagard®-200 HD WB to come in contact with any glass, fabric, metal, or painted surfaces.

- Immediately wipe contaminated surfaces with a clean water-saturated cloth, then wipe dry with a second clean cloth.
- Allow at least 7 days after application before using adhesives over Sikagard®-200 HD WB.
- One application of Sikagard®-200 HD WB is normally sufficient. Repeat applications will ensure complete densification of concrete surface.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit usa.sika.com to verify the most current versions.
- Proper application is the responsibility of the user.
   Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the job site.

#### SUBSTRATE PREPARATION

#### **New Concrete**

- 1. Freshly finished concrete surfaces require no surface preparation if Sikagard®-200 HD WB is applied immediately after the final finishing operation in place of a resin or acrylic curing compound.
- 2. On areas where forms have been recently removed, all form oil or breaking compound residue must be removed prior to application.

#### Existing Concrete (Cured 28 Days or Longer)

- 1. Remove all dust and dirt, and ensure the surface is completely dry.
- 2. The surface must be free from all contaminants to allow penetration of Sikagard®-200 HD WB into the pores of the concrete.
- If acid is used to remove surface coatings, the acid must be neutralized and the surface flushed with water and allowed to dry completely before application of Sikagard®-200 HD WB.
- 4. Apply Sikagard®-200 HD WB to a test area to verify effectiveness and final surface finish

#### **APPLICATION**

Sikagard®-200 HD WB must fully saturate the concrete for maximum effect. Apply sufficient product to saturate the concrete without puddling.

#### **New Concrete**

1. After final finishing, as soon as all surface water has



evaporated and the concrete can bear foot traffic, apply Sikagard®-200 HD WB with a low-pressure sprayer. Keep the entire surface wet with Sikagard®-200 HD WB for a full 30 minutes by spraying or by brooming excess material from low spots to saturate dry spots.

- As Sikagard®-200 HD WB begins to penetrate into the surface, lightly sprinkle the surface with water to aid penetration.
- 3. When the surface begins to dry a second time, flush with water and use a squeegee or broom to remove excess material or impurities that may have been brought to the surface.
- 4. To improve sheen, dry buff with a non-abrasive pad the following day.

Existing Concrete (Cured 28 Days or Longer)

- Saturate the surface with undiluted Sikagard®-200 HD WB. Keep the entire surface wet with Sikagard®-200 HD WB for a full 30 minutes by spraying or by brooming excess material from low spots to saturate dry spots.
- After 30-40 minutes, if most of the Sikagard®-200 HD WB has been absorbed into the surface, broom or squeegee any excess material from the low spots so it may be absorbed into the surface or completely removed from it. Flush floor clean with water.
- 3. Alternatively, use a floor buffing machine with a nonabrasive pad to help work Sikagard®-200 HD WB into fully cured concrete during application.

#### **CLEANING OF TOOLS**

Clean brushes, tools and equipment with clean water immediately after use. Thoroughly flush sprayers. Dispose of unused material according to local regulations.

#### LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at https://usa.sika.com/en/group/SikaCorp/termsandconditions.html or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue Lyndhurst, NJ 07071 Phone: +1-800-933-7452 Fax: +1-201-933-6225 usa.sika.com



Product Data Sheet
Sikagard®-200 HD WB
September 2024, Version 02.01
020815110010000059

